

polyethylene

NOVAPOL® HB-W952-A Resin

Hexene Copolymer HDPE Blow Molding Resin



product data sheet

Property	ASTM ⁽¹⁾	Typical Values ⁽²⁾
High Load Melt Index ⁽³⁾	D 1238	10.0 g/10 min
Density	D 792	0.952 g/cm ³
		METRIC UNITS ENGLISH UNITS

Molded Plaque Properties

Yield Strength	D 638	25 MPa	3,600 psi
Elongation	D 638	820 %	820 %
Flexural Modulus	D 790	1,280 MPa	185,600 psi
Tensile Impact	D1822	32 J/cm ²	152 ft-lb/in ²
Low Temperature Brittleness Point	⁽⁴⁾ D 746	< -70 °C	< -94 °F
ESCR, (F ₅₀)	⁽⁵⁾ D 1693	> 1 000 h	
ESCR, (F ₅₀)	⁽⁶⁾ D 1693	> 1 000 h	
Izod Impact	⁽⁷⁾	3.9 J/cm	7 ft-lb/in

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/21.6 kg.

(4) F50, notched specimen.

(5) Environmental stress crack resistance, Condition A, 100% Igepal.

(6) Environmental stress crack resistance, Condition B, 100% Igepal.

(7) 3.2 mm (0.125 in) thick specimen.

HL Melt Index 10.0

Density 0.952

Features

- High molecular weight HDPE
- Excellent ESCR
- Impact strength
- High rigidity
- Good processability

Additives

- Process stabilizer

Applications

- General large-part blow molding
- Trash cans
- Drums
- Jerry cans
- Fuel tanks
- Corrugated land drainage pipe

PRODUCT DATA SHEET

NOVAPOL HB-W952-A Resin

Hexene Copolymer HDPE Blow Molding Resin

Availability

NOVAPOL HB-W952-A polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

NOVAPOL HB-W952-A resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Material Safety Data Sheet (MSDS) contains important safety information and should be reviewed before using the product.

Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Food Packaging Status

United States: NOVAPOL HB-W952-A resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without temperature or food-type restrictions, subject to technical suitability.

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



Is the SPI resin code developed for high density polyethylene to identify material type for sorting and recycling purposes.

 is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.
NOVAPOL® is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

August 14, 2013